

## HT870 Flame Retardant Silicone Sponge Sheet

*Our softer density silicone sponge sheets have better compressibility and protection making them suitable for vibration dampening and cushioning. The softer material creates a refined seal line without excessive force, useful for delicate applications such as electronic equipment housing. The compressibility also allows for more flexibility in gasket or seal design because the material will conform to variable width gaps and awkward shapes. This rubber sheeting is available with pressure sensitive adhesive backing. Polymax also provide a fabrication service to create gaskets or strips - please call us for more information.*

### Approvals

Various thicknesses meet different EN 45545 specifications, please view each product datasheet for more information. Compliant with GENERAL MOTORS GMW16392 Type 1 and UL 94 V-0 HF-1.

**Operating temperature range: -55°C to 200°C**

Physical Property	Test Method	Units	Typical Values
Elongation at Break	ASTM D412	%	90
Tensile Strength	ASTM D412	MPa	0.207
Compression Set ASTM D 1056 Test D @ 70°C		%	<1
Flame Resistance	UL 94		Listed V-0 and HF-1
Flame Spread Index	ASTM E162	Ls	<25
Smoke Density @ 4 Minutes	ASTM E 662	Ds	<50
Toxic Gas Emissions Rating	SMP-800C		Pass
Water Absorption	Internal: 24hrs @ room temp	%	2.5
UV Resistance	SAE J - 1960		No Degradation
Ozone Effect Rating	ASTM D 1171		No Cracks
Corrosion Resistance	AMS - 3568		Pass
Dielectric Constant	ASTM D 150		1.38
Dialectric Strenght	ASTM D 149	Volts/mil	90
Dry Arc Resistance	ASTMD 485	Seconds	91
Volume Resistivity	ASTM D 257	Ohm-cm	10 <sup>14</sup>
Thermal Conductivity	ASTM C 518	w/m <sup>°K</sup>	0.07

Although the technical details and recommendations made correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use Polymax products must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product. All sales subject to our standard terms [www.polymax.co.uk/sales-terms](http://www.polymax.co.uk/sales-terms)