

## SILONA High Temp Red 1000mm x 6mm 60ShA

**Product SKU: 3043903**


High temperature silicone sheeting suitable for working conditions up to 300°C. Sold in linear meter lengths. FDA Complies with Food & Drugs Association Silicone sheeting has no resistance to oils. Available with pressure sensitive adhesive backing and fabrication service to create gaskets or strips - please call us for more information.

**Colour: Red**

**Material: Silicone**

**Operating temperature range: -60°C to 300°C**

FDA Standard 21 CFR 177.2600, FAR 25/ JAR 25 /CS 25 Horizontal Flammability Tests, Automotive Standard Part 571MVSS302, EU 1935/2004, REACH and RoHS.



Physical Property	Test Method	Units	Typical Values
Hardness	ASTM D412	ShA	60
Elongation at Break	ASTM D412	%	350
Tensile Strength	ASTM D412	MPa	9
Tear Resistance	ASTM D412	kN/m	22
Compression Set 24hrs @150		%	11
Brittle Point	ASTM D746	°C	-80
Thermal Conductivity	VDE 0304	W.m <sup>-1</sup> .K. <sup>1</sup>	0.24
Limiting Oxygen Index	BS 2782 Part 1	%	24
Radiation Resistance		Grays	>105
Dielectric Strength	VDE 0303	kV.mm-1	23
Dielectric Constant	VDE 0303		2.9
Dissipation Factor	VDE 0303		3x10 <sup>-4</sup>
Volume Resistivity	VDE 0303	ohms.cm	3x10 <sup>15</sup>

Although the technical details and recommendations made correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use Polymax products must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product. All sales subject to our standard terms [www.polymax.co.uk/sales-terms](http://www.polymax.co.uk/sales-terms)